








TECHNISCHE WERTE
 TECHNICAL SPECIFICATIONS
 ТЕХНИЧЕСКИЕ ДАННЫЕ
 SCHEDA TECNICA

ZEITLOS

DIN EN 14411

Bezeichnung/Description/ Обозначение артикула/Descrizione	Format/Size/Обозначение артикула/ Formato	Artikelnummer/Order number/ номер артикула/Articolo	Farbe/Colour/Liçer/Colore
Klinkerriemchen	240 x 71 x 14 mm	7470	237 austerrauch, 351 kalkbrand, 352 kupferschmelz, 353 eisenrost, 354 bronzebruch, 355 sandschmelz, 356 erdfeuer, 357 backstein, 359 kohleglanz, 360 onyxstaub, 368 sepiaquarz
Klinkerriemchen	400 x 71 x 14 mm	7440	237 austerrauch, 351 kalkbrand, 353 eisenrost, 355 sandschmelz, 357 backstein, 359 kohleglanz
Klinkerriemchen	400 x 35 x 14 mm	7435	237 austerrauch, 351 kalkbrand, 353 eisenrost, 355 sandschmelz, 357 backstein, 359 kohleglanz

	Wasseraufnahme (Mittelwert) Water absorption (Average value) Водопоглощение (среднее значение) Assorbente acqua (Valore medio) (EN ISO 10545-3):	≤ 3 %
	Ritzhärte nach Mohs (kleinster Einzelwert) Scratch hardness of surface (Mohs scale) (minimum individual value) Твердость по шкале Мооса (меньшее значение) Durezza sclerometrica sec. Mohs (valore singolo minore) (EN 15771):	6-7
	Frostbeständigkeit frost resistance Морозоустойчивость Resistenza al gelo (EN ISO 10545-12):	erfüllt/is fulfilled/Выполнено/conforme
	Chemische Beständigkeit – außer gegen Flußsäure und ihre Verbindungen – für Fliesen und Platten Chemical resistance – except to hydrofluoric acid and its compounds – of tiles Химическая устойчивость — кроме плавиковой кислоты (фтористоводородной) и ее соединений — для глазурованной и неглазурованной плитки Resistenza agli agenti chimici – ad eccezione dell' acido fluoridrico e dei suoi composti – per piastrelle (EN ISO 10545-13):	erfüllt/is fulfilled/Выполнено/conforme
	Temperaturwechselbeständigkeit Thermal shock resistance Термостойкость Resistenza agli sbalzi di temperatura (EN ISO 10545-9):	erfüllt/is fulfilled/Выполнено/conforme
	Thermischer LAK von Raumtemperatur (20° C) bis 100° C Coefficient of thermal expansion from room temperatur (20° C) to 100° C/CE Коэффициент термического расширения от комнатной температуры (20° C) до 100° C Coefficiente di dilatazione in lunghezza a temperatura ambiente (20° C) fino a 100°C (EN ISO 10545-8):	< 80x10 ⁻⁷ K ⁻¹
	Porenradienmaximum (Soll: rp > 0,2 µm) Maximum pore radius (required: rp > 0,2 µm) Максимальный радиус пор (Требуемое: rp > 0,2 µm) Raggio massimo dei pori (richiesto: rp > 0,2 µm) (DIN 66 133):	0,54 µm – 6,24 µm

TECHNISCHE WERTE
TECHNICAL SPECIFICATIONS
ТЕХНИЧЕСКИЕ ДАННЫЕ
SCHEDA TECNICA

ströher[®]
Klinker. Keramik. Macher.



Porenvolumen (Soll: $V_q > 20 \text{ mm}^3/\text{g}$)
Pore volume (required: $V_q > 20 \text{ mm}^3/\text{g}$)
Объем пор (Требуемое: $V_q > 20 \text{ mm}^3/\text{g}$)
Volume dei pori (richiesto: $V_q > 20 \text{ mm}^3/\text{g}$)
(DIN 66 133):

21,3 mm^3/g – 47,0 mm^3/g

Ströher GmbH
Ströherstraße 2-10
35683 Dillenburg
Telefon: +49 2771 391-0
Telefax: +49 2771 391-340
E-Mail: info@stroeher.de
www.stroeher.de

Ströher GmbH
i. V. Jochen Keil
Laborleiter